

**PAT-NO:** JP409235543A  
**DOCUMENT-IDENTIFIER:** JP 09235543 A  
**TITLE:** SEALING MATERIAL  
**PUBN-DATE:** September 9, 1997

**INVENTOR-INFORMATION:**

NAME	COUNTRY
------	---------

WADA, HIROSHI	
YAMAMOTO, HIROSHI	
SOEDA, YOSHIKAZU	
MATSUOKA, NAOKI	
TOKUNAGA, YASUYUKI	
ANDO, MASAHIKO	

**INT-CL** C09K003/10 , C09J007/02 , C09J007/02 , C09J007/02 ,  
**(IPC):** C09J007/02 , C09J007/02

**ABSTRACT:**

PROBLEM TO BE SOLVED: To obtain a sealing material consisting of a sealing substrate and a specific tacky adhesive composition layer formed on the substrate, exhibiting excellent releasability from a releasing liner and the own back surface of the material even by using a releasing liner or sealing substrate free from silicone treatment and having high adhesive force and sealing effect.

SOLUTION: This material is produced by forming (A) a layer of a tacky adhesive composition containing a polymer having a polycarbonate structure having a recurring unit of formula [R is a 2-20C (branched)hydrocarbon group] (e.g. a polymer composed mainly of a polyester having a weight average molecular weight of  $\geq 10,000$  and derived from a diol component containing polycarbonate diol as an essential component and a dicarboxylic acid component containing dicarboxylic acid having a molecular skeleton consisting of a 2-20C aliphatic or alicyclic hydrocarbon group as an essential component) on (B) a sealing substrate (e.g. a sheet or foamed material of a synthetic resin or a synthetic rubber or a laminate of these synthetic resin films).

COPYRIGHT: (C)1997,JPO

**PAT-NO:** JP404103686A  
**DOCUMENT-IDENTIFIER:** JP 04103686 A  
**TITLE:** HOT-MELT ADHESIVE  
**PUBN-DATE:** April 6, 1992

**INVENTOR-INFORMATION:**

NAME	COUNTRY
------	---------

NAKANO, MANABU	
----------------	--

TANAKA, JIRO	
--------------	--

ISHIGURO, MICHIIHIRO	
----------------------	--

AKAZAWA, TOSHIYUKI	
--------------------	--

**INT-CL (IPC):** C09J175/04 , C08G018/32

**US-CL-CURRENT:** 526/935

**ABSTRACT:**

**PURPOSE:** To provide the subject adhesive composed of a polyurethane having specific physical properties and produced by reacting a high-molecular diol, a low-molecular dial and a diisocyanate, having excellent adhesive strength and bonding workability and suitable for the bonding of plastic, cloth, rubber, etc.

**CONSTITUTION:** The objective adhesive is composed of a polyurethane produced by reacting (A) a high-molecular diol such as polyester diol and polycarbonate diol, (B) a low-molecular diol of formula ((n) is integer of 6-12) and (C) a diisocyanate. The polyurethane has a weight-average molecular weight of preferably 100,000-450,000 and exhibits one or more melting peaks in differential scanning thermal analysis, wherein the temperature of the peak of the highest temperature is 90-140°C and the heat of fusion of the peak is 8-20J/g.

**COPYRIGHT:** (C)1992, JPO&Japio

**PAT-NO:** JP410081085A  
**DOCUMENT-IDENTIFIER:** JP 10081085 A  
**TITLE:** PROTECTIVE SHEET FOR TAMPERING PREVENTION AND METHOD THEREFOR  
**PUBN-DATE:** March 31, 1998

**INVENTOR-INFORMATION:**

NAME	COUNTRY
ANDO, MASAHIKO	
TOKUNAGA, YASUYUKI	
YAMANAKA, TAKESHI	
HIKOSAKA, WAKA	

**INT-CL (IPC):** B42D015/10 , C09J169/00

**ABSTRACT:**

PROBLEM TO BE SOLVED: To surely and easily prevent the expressions of bonds and the like and the contents of containers and the like from being altered without trouble on workability and the like by a method wherein this protective sheet consists of a support and a self-adhesive layer and the self-adherent force between the self-adhesive layers is set to have the specified value.

SOLUTION: This protective sheet consists of a support and a self-adhesive layer and the self-adherent force between the self-adhesive layers is set to be 2kg/20mm of width or more. The self-adhesive layer is made of polyester of polycarbonate diol and dicarboxylic acid, especially diol component containing polycarbonate diol as essential one and dicarboxylic acid component containing dicarboxylic acid having 2-20C aliphatic or alicyclic hydrocarbon group as molecular skeleton as essential one and preferably has the weight average molecular weight of 20,000 or more. Accordingly, when a bond, a container or the like is covered with the protective sheet and its peripheral edges are pasted together through the self-adhesives, the peripheral edges do not easily separate from each other and, even when separated under the condition that printing or the like is performed on the self-adhesive layer surface, the getting out of shape of the printing becomes remarkable, resulting in allowing to easily discriminate the alteration of the expression, contents and the like.

COPYRIGHT: (C)1998, JPO